
















VINYL LONGUS

| | | | HDF | Tiles |
|--|--------------------------------|-----------------|--|--|
|  | Dimensions & thickness | EN 427 & EN 428 | ca. 1815 × 230 × 10,0 mm ca. 1815 × 305 × 10,0 mm | ca. 1815 × 230 × 2,0 mm ca. 1815 × 305 × 2,0 mm |
|  | Classification | EN 16511 | domestic 23 commercial 33 | domestic 23 commercial 33 |
|  | Total weight | EN 430 | ca. 10.000 g/m ² | ca. 3.600 g/m ² |
|  | Impact sound reduction | EN ISO 717-2 | ca. 16 dB | ca. 5 dB |
|  | Effect of castor chair | EN 425 | suitable for type W | suitable for type W |
|  | Reaction of fire | EN ISO 9239-1 | Bfl s1 | Bfl s1 |
|  | Thermal resistance | EN 12524 | 0,088 m ² K/W | ca. 0,019 m ² K/W |
|  | Dimensional stability | EN 434 | < 0,05% | < 0,10% |
|  | Residual indentation | EN 433 | max. 0,03 mm | max. 0,03 mm |
|  | Lightfast | ISO 105 | 6 / 7 | 6 / 7 |
|  | Resistance to chemicals | EN 423 | Good resistance | Good resistance |
| | Emissions value | | in conformity with AgBB | in conformity with AgBB |
|  | Swellness value 24h | EN 317 | < 8% | 0 % (wasserfest / waterproof) |
|  | Locking strength | ISO 24334 | HDF > 500 kg/lfm – kg/m | |
|  | Reaction to static electricity | EN 1815 | < 2,0 kV | < 2,0 kV |
|  | Coefficient of friction | EN 51130 | R10 | R10 |

