















REAL DESIGNWOOD

			HDF
	Dimensions & thickness	EN 427 & EN 428	ca. 1235 × 200 × 9,6 mm
	Classification	EN 16511	domestic 23 commercial 33
	Total weight	EN 430	ca. 7600 g/m ²
	Abrasion resistance	EN 14354 & EN 13329	> 8000 Umdrehungen / turns / WR 4 AC 5
	Impact sound reduction	EN ISO 717-2	15 dB
	Effect of castor chair	EN 425	Suitable
	Reaction of fire	EN ISO 9239-1	Cfl s1
	Thermal resistance	EN 12524	ca. 0.102 m ² K/W
	Dimensional stability	EN 434	< 0,05 %
	Residual indentation	EN 433	max. 0.05 mm / Klasse 33
	Resistance to chemicals	EN 423	very good resistance
	Emissions value		in conformity with AgBB
	Locking strength	ISO 24334	HDF > 500 kg/lfm – kg/m
	Micro scratch resistance	EN 16094	MSR – A1 / MSR – B1 / Klasse 33
	Slip resistance	EN 13501 -1	Klasse DS / R10
	Effect of stains	EN 438-2:2016	Grad 5 / 5

