




OUTEX DESIGN

			Decking	Tiles 300 x 300	Tiles 600 x 300
	Dimensions & thickness	EN 427 & EN 428	ca. 2000 × 96 × 21,5 mm	ca. 300 × 300 × 30 mm	ca. 600 × 300 × 30 mm
	Tiles		Thermo Pine	Thermo Pine Thermo Beech	Thermo Pine Thermo Beech
	Reaction to static electricity	EN 1815	< 2 kV = antistatic	< 2 kV = antistatic	< 2 kV = antistatic
	Effect of stains	EN 438-2:2016	Grad 5	Grad 5	Grad 5
	Temperature resistance		No alterations between -25°C and +80 °C	No alterations between -25°C and +80 °C	No alterations between -25°C and +80 °C
	Fire resistance	EN ISO 11925-2	Euroclass E (B2)	Euroclass E (B2)	Euroclass E (B2)
	Resistance of water		Swelling after 24h: <0,05%	Swelling after 24h: <0,05%	Swelling after 24h: <0,05%
	UV ray resistant	ISO 105	Grad 7/8	Grad 7/8	Grad 7/8
	Spots and chemical substances resistance	EN 438	Grad 5 (Groups 1, 2, 3)	Grad 5 (Groups 1, 2, 3)	Grad 5 (Groups 1, 2, 3)
	Formaldehyde emission	EN 717	E1	E1	E1
	Fungus resistance	ASTM G21	No attack after 28 days	No attack after 28 days	No attack after 28 days
	Slipperiness barefoot	DIN 51097:1992	B (A+B – slip angle 22,2°)	B (A+B – slip angle 22,2°)	B (A+B – slip angle 22,2°)
	Slipperiness	DIN 51130:2014	R10	R10	R10
	Slipperiness	UNE-ENV 12633:2003	Class 2	Class 2	Class 2

